

Di-n-Octyl phthalate(DOP) Analysis

1. Analytical Condition

YL 6500 Series

Oven : 40°C(3min)->10°C/min->280°C(3min)

Column : HP-1 (30m*0.32mm*0.5um)

Carrier gas : He, 1.5ml/min (Split ratio 150:1)

Injector : Capillary 300°C

Detector : FID 300°C

Injection Volume : Injection volume 0.8ul

2. Chromatogram

