

PMMA (THF GPC)

1. Analytical Condition

YL 9100 Series

Sample : Polymethylmethacrylate MW 6,400,000 / 520,000 / 2,540

Mobile phase : THF

Flow rate : 0.8 mL/min

Injection : 20 μ l

Column oven : 35°C

Detector : RID 35 °C

Column : Styragel Guard column(THF) / Styragel THF HR 5E / 4 / 3

2. Chromatogram

