

Polystyrene(THF GPC)

1. Analytical Condition

YL 9100 Series

Sample : Polystyrene STD MW 4,230,000 / 219,000 / 30,300 / 1,200

Mobile phase : THF

Flow rate : 1 mL

Column oven : 35°C

Detector : UVD 254nm

Column : Styragel THF HR 5E / 4E / 1

2. Chromatogram

